Technical Data Sheet

Moplen HP526J

Polypropylene, Homopolymer



Product Description

Moplen HP526J is a polypropylene homopolymer designed for the production of biaxially oriented polypropylene films (BOPP). The product is suitable for metallizable film, both as monolayer film and in coextruded structures. It contains a standard processing stabilisation but does not contain any slip, antiblocking agents and it is Calcium Stearate free. Moplen HP526J offers good optical, excellent & highly consistent processing and very good film profile. Typical applications are BOPP packaging film and sheet for Solid Phase Thermoforming.

Regulatory Status

For regulatory compliance information, see *Moplen* HP526J <u>Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS)</u>.

Status Commercial: Active

Availability Africa-Middle East; Europe

Application Barrier Film; Food Packaging Film; Thermoformed Food Containers

MarketFlexible PackagingProcessing MethodBOPP; Thermoforming

Attribute Good Optical Properties; Good Processability; High Clarity; High Gloss; Homopolymer

| | Nominal | | |
|---|---------|----------|---------------|
| Typical Properties | Value | Units | Test Method |
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 3.0 | g/10 min | ISO 1133-1 |
| Density | 0.90 | g/cm³ | ISO 1183-1 |
| Mechanical | | | |
| Flexural Modulus | 1450 | N/mm² | ISO 178 |
| Tensile Stress at Break, (23 °C, 50 mm/min) | 23 | N/mm² | ISO 527-1, -2 |
| Tensile Stress at Yield, (23 °C, 50 mm/min) | 34 | N/mm² | ISO 527-1, -2 |
| Tensile Strain at Break, (23 °C, 50 mm/min) | >=500 | % | ISO 527-1, -2 |
| Tensile Strain at Yield, (23 °C, 50 mm/min) | 12 | % | ISO 527-1, -2 |
| Hardness | | | |
| Shore Hardness, (Shore D) | 70 | | ISO 868 |
| Thermal | | | |
| Vicat Softening Temperature, (A50) | 154 | °C | ISO 306 |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 85 | °C | ISO 75B-1, -2 |

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

LyondellBasell Technical Data Sheet Date: 1/30/2023 Moplen HP526J Recipient Tracking #: Request #: 4170210